

EPDM Moosgummi Rundschnur schwarz • EPDM foam rubber cord black



gemischtzellig

mixed cellular

Dichte • Specific gravity

0,5 \pm 0,1 g / cm³ • DIN 53479

Farbe • Color

schwarz • black •

Temperatur • Temperature range

-35 bis 110 °C •

Abmessung	Toleranz	Breite	Länge
mm	mm	mm	mm
2,0	+0,5	-	200.000
2,5	+0,5	-	200.000
2,8	+0,7	-	200.000
3,0	+0,7	-	200.000
3,5	+0,7	-	200.000
4,0	+0,7	-	200.000
4,5	+0,8	-	200.000
5,0	+0,8	-	200.000
6,0	+0,8	-	200.000
7,0	+1,0	-	200.000
8,0	+1,0	-	200.000
9,0	+1,0	-	200.000
10,0	+1,0	-	200.000
11,0	+1,3	-	200.000
12,0	+1,3	-	200.000
15,0	+1,3	-	50.000
16,0	+1,3	-	50.000
18,0	+1,6	-	50.000
20,0	+1,6	-	25.000

Technische Daten gemessen bei 20°C / Die Angaben dieses Datenblattes sind das Ergebnis langjähriger Erfahrungen. Die Angaben stellen keine Eigenschaftszusicherung dar und befreien nicht von der eigenen Prüfung der von uns gelieferten Produkte auf deren Eignung für den vorgesehenen Einsatzfall. Sie haben somit nicht die Bedeutung, bestimmte Eigenschaften der Produkte oder deren Eignung für einen konkreten Einsatzzweck rechtlich verbindlich zu versichern.

Technical data measured with 20°C / The technical data of this data sheet are the result of experiences of many years. The data represent no characteristics warranties and do not release from the own examination the products on their suitability for intended case of application, supplied by us. They do not have thus the meaning to assure certain characteristics of the products or their suitability obligatorily on a concrete targeted application legally.

Abmessung	Toleranz	Breite	Länge
mm	mm	mm	mm
22,0	+1,6	-	25.000
25,0	+1,6	-	25.000
30,0	+2,0	-	20.000
35,0	+2,0	-	20.000
40,0	+2,0	-	20.000
45,0	+2,5	-	20.000
60,0	+2,5	-	20.000

Technische Daten gemessen bei 20°C / Die Angaben dieses Datenblattes sind das Ergebnis langjähriger Erfahrungen. Die Angaben stellen keine Eigenschaftszusicherung dar und befreien nicht von der eigenen Prüfung der von uns gelieferten Produkte auf deren Eignung für den vorgesehenen Einsatzfall. Sie haben somit nicht die Bedeutung, bestimmte Eigenschaften der Produkte oder deren Eignung für einen konkreten Einsatzzweck rechtlich verbindlich zuzusichern.

Technical data measured with 20°C / The technical data of this data sheet are the result of experiences of many years. The data represent no characteristics warranties and do not release from the own examination the products on their suitability for intended case of application, supplied by us. They do not have thus the meaning to assure certain characteristics of the products or their suitability obligatorily on a concrete targeted application legally.