

# **PA 6 G LFX**

**Chem. Designation:** Polyamid

**DIN-Abbreviation:** PA 6 G LFX

<b>Properties</b>		<b>Value</b>	<b>Unit</b>	<b>ISO/IEC</b>
Density		1,135 / -		
Water absorption absolutely 1)		44 / 83	mg	62
Water absorption, relative 1)		0,66 / 1,24	%	62
- at saturation in air of 23°C, 50% RF		2 / -	%	
- at saturation in water of 23°C		6,3 / -	%	
<b>Thermal Properties</b>		<b>Value</b>	<b>Unit</b>	<b>ISO/IEC</b>
Crystalline melting point		220 / -	°C	-
Thermal conductivity (23° C)		0,28 / -	W/(k·m)	-
Coefficient of thermal expansion: - average value between 23 and 60°C		80 · 10^-6 / -	m/(m·K)	-
Coefficient of thermal expansion: - average value between 23 and 100°C		90 · 10^-6 / -	m/(m·K)	-
Temperature of deflection under load - Method a: 1,8 MPa		75 / -	°C	75
Max. service temperature in air: -short periods 2		165 / -	°C	-
Max. service temperature in air: -continuously: for min. 5000/20.000 h		105 / 90	°C	-
Minimum service temperature		-20 / -	°C	-
Flammability acc. to UL standard 94 (thickness 3mm/6mm)		HB / HB		-
<b>Mechanical Properties (at 23°C)</b>		<b>Value</b>	<b>Unit</b>	<b>ISO/IEC</b>
Tensile strength at yield/Tensile strength at break	dry	70 / -	MPa	527-1/-2
Tensile strength at yield/Tensile strength at break	moist	45 / -	MPa	527-1/-2
Elongation at break	dry	25 / -	%	527-1/-2
Elongation at break	moist	>50 / -	%	527-1/-2
Modulus of elasticity in tension	dry	3000 / -	MPa	527-1/-2
Modulus of elasticity in tension	moist	1450 / -	MPa	527-1/-2
Compression Test - 1% nominal strain	dry	22 / -	MPa	604
Tensile creep 3)	dry	18 / -	MPa	899
Tensile creep 3)	moist	8 / -	MPa	899
impact-strength - Charpy unnotched	dry	50 / -	kJ/m²	179/1eU
impact-strength Charpy notched	dry	4 / -	kJ/m²	179/1eA
impact-strength Izod	dry	4 / 40	kJ/m²; J/m	180/2A
impact-strength Izod	moist	7 / 70	kJ/m²; J/m	180/A
Ball indentation hardness H 358 / 30 or H 961 / 30	dry	145 / -	N/mm²	2039-1
Hardness, Rockwell	dry	M82 / -		2039-2
Coefficient of Friction 4)	dry	0,2 / 0,35	μ	
<b>Electrical Properties</b>		<b>Value</b>	<b>Unit</b>	<b>ISO/IEC</b>
Dielectric strength	dry	22 / -	kV/mm	60243
Dielectric strength	moist	14 / -	kV/mm	60243
Volume resistivity	dry	10^14 / -	Ohm·cm	60093
Volume resistivity	moist	10^12 / -	Ohm·cm	60093
Surface resistivity	dry	10^13 / -	Ohm	60093
Surface resistivity	moist	10^12 / -	Ohm	60093
Dielectric constant at 100 Hz	dry	3,5 / -		60250
Dielectric constant at 100 Hz	moist	6,5 / -		60250
Dielectric constant at 1 MHz	dry	3,1 / -		60250
Dielectric constant at 1 MHz	moist	3,6 / -		60250
Dielectric dissipation factor tan δ at 100 Hz	dry	0,015 / -		60250
Dielectric dissipation factor tan δ at 100 Hz	moist	0,15 / -		60250

# PA 6 G LFX

**Chem. Designation:** Polyamid**DIN-Abbreviation:** PA 6 G LFX

Dielectric dissipation factor tan δ at 1 MHz	dry	0,016 / -	60250
Dielectric dissipation factor tan δ at 1 MHz	moist	0,05 / -	60250
Comparative tracking index (CTI)	dry	CTI 600 / -	CTI 60112
Comparative tracking index (CTI)	moist	CTI 600 / -	60112

dry = values referring to dry materials  
moist = values referring to material in equilibrium with  
          = the standard atmosphere 23°C/50% RH  
o.B. = no break

1) after 24/96h immersion in water of 23°C  
2) only for short time exposure (a few hours) in applications where no or only a very  
   low load is applied to the material  
3) stress to produce 1% strain in 1000 h (s 1/1000)  
4) p = 0,05 N/mm<sup>2</sup>, v= 0,6 m/s surface roughness C35 steel mating surface Ra 0,7 - 0,9

This table is a valuable help in the choice of material. The data listed here fall within the normal range of product properties. However, they are not guaranteed and they should not be used to establish material specification limits nor used alone as the basis of design. It has to be noted that fibre reinforced material shows an anisotropic behaviour (properties differ when measured parallel and perpendicular to the extrusion direction).